SILITECH

SILISIL RTV MF-Soft 12

Technical product information · 10.11.2026

Pourable, addition-curing silicone for pad printing.

Typical technical values

Mixing ratio	1:1 by weight
Colour	Blue
Viscosity of the mixture	3’500 mPa·s
Density at 23 °C	1,1 g/cm³
Working time at 23 °C	20 min
Setting time at 23 °C	90 min
Hardness after 24 h at 23 °C	12 Shore A
Tensile strength	3 N/mm²
Elongation at break	550 %
Tear strength	8,6 N/mm (Die B)

Processing

Weigh the matching components and mix thoroughly, including the sides and bottom of the container. Use clean, dry mixing equipment. Working time and setting time start when the components are combined and refer to 23 °C. Higher or lower temperatures change the process.

Notes

Read the safety data sheets for all components before processing. Close containers after use.

The figures are typical technical values. Unless otherwise indicated in the table, mechanical properties refer to material vulcanised for 24 hours at 23 °C. Verify suitability for the intended application in preliminary trials.